512 OPTICAL FIBRES CABLE FOR DUCT INSTALLATION - KP TYPE











STANDARDS

Construction: Telefónica standard ERQ.f6.0227- Edition 1

Fibre: ITU-T G652D

DESCRIPTION AND APPLICATION

Loose tube single mode Optical Cable, totally dielectric with 512 fibers. The tubes are filled with a thixotropic filling compound. Waterblocking beteen the tubes is achieved by swellable dry elements. The core is protected by an aramid reinforced PE sheath. Installation in ducts by pulling or blowing.

CONSTRUCTION

- Central reinforcing element: Dielectric fibreglass (FRP).
- **Loose tubes**: PBT loose tubes filled with thixotropic compound with 32 optic fibres. Colour coding of tubes and fibres according to tables 1 and 2.
- *Core formation*: Loose tubes stranded in SZ. Swellable yarns and tapes to avoid water penetration and make the cable waterproof.
- Reinforcement: Aramid yarns as reinforcing element.
- Outer sheath: Black polyethylene, UV resistant.
- **Sheath marking**: The cable sheath will be marked with white ink at regular intervals with the following information:
 - CABLESCOM / year / Number of fibres MN/batch number/Single mode fibre (MN)/ sheath type (KP) /length markings
 - o Other sheath marks available upon request





OPTICAL FIBRE CHARACTERISTICS

The parameters of the optical fibres are compliant with the ITU-T G.652D recommendation. See our fibre product sheet for the characteristics of the fibre

Optical transmission characteristics of cabled fibre ::

Attenuation coefficient:

Average / maximum at 1310 nm: 0,36 / 0,38 dB/km Average / maximum at 1550 nm: 0,22 / 0,26 dB/km

 $PMD \le 0,20 \text{ ps/km}^{1/2}$ $PMD \text{ link} \le 0,10 \text{ ps/km}^{1/2}$

Cut-off wavelength $(\lambda_{cc}) \leq 1260$ nm

All drawings, designs, specifications and particulars of weights, dimensions, etc. in this documentation are only indicative and must not be considered contractual.

512 OPTICAL FIBRES CABLE FOR DUCT INSTALLATION - KP TYPE

TABLE 1: LOOSE TUBES COLOUR CODE

| | Number of tubes in layer | | | | | | | | | | | |
|-----------------------|--------------------------|-------|-------|------|-------|-------|------|------|------|-------|-------|-------|
| | 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | 9 | 10 | 11 | 12 |
| 1 st Layer | White | Red | Black | Blue | Verde | Black | | | | | | |
| 2 nd layer | White | White | White | Red | Red | Red | Blue | Blue | Blue | Green | Green | Green |

^{*}Note: Black tubes are fillers

TABLE 2: OPTICAL FIBERS COLOUR CODE

| .Fibre | Colour | | Fibre | Colou | r |
|--------|----------|--|-------|------------|------|
| 1 | Green | | 17 | Green ** | |
| 2 | Red | | 18 | Red ** | |
| 3 | Blue | | 19 | Blue ** | |
| 4 | Yellow | | 20 | Yellow** | |
| 5 | Grey | | 21 | Grey ** | |
| 6 | Violet | | 22 | Violet ** | |
| 7 | Brown | | 23 | White ** | |
| 8 | Orange | | 24 | Orange ** | |
| 9 | Green * | | 25 | Green *** | |
| 10 | Red * | | 26 | Red *** | 111 |
| 11 | Blue* | | 27 | Blue *** | |
| 12 | Yellow * | | 28 | Yellow *** | -111 |
| 13 | Grey * | | 29 | Grey *** | |
| 14 | Violet * | | 30 | Violet *** | |
| 15 | White * | | 31 | White *** | |
| 16 | Orange * | | 32 | Orange *** | |

^{(*):} fibres from 9 to 16 are marked with a black ring approximately every 50 mm.

(**): fibres from 17 to 24 are marked with a double black ring approximately every 50 mm.

(* * *): Fibres from 25 to 32 are marked with a triple black ring approximately every 50 mm.

| MECHANICAL CHARACTERISTICS | Specifications | Test conditions |
|---|----------------------|-------------------------------------|
| Tensile strength (Δεf=0%, Δα<0.05 dB) | EN 187000, Met. 501 | 3500 N |
| Maximum tensile strength (Δεf<0,33%, Δα reversible) | | 6500N |
| Impact resistance (Δα<0.05 dB) | EN 187000, Met. 505 | 5J, R = 10mm |
| Crush resistance (Δα<0.05 dB) | EN 187000, Met. 504 | 2000 N |
| Static bending (Δα<0.05 dB) | EN 187000, Met. 513 | r =15d mm, 3 cycles |
| Repeated bending (Δα<0.05 dB) | EN 187000, Met. 507 | r =15d mm, 100 cycles |
| Torsion test (Δα<0.05 dB) | EN 187000, Met. 507 | ±360º, 100 N, 5 cycles |
| Temperature cycling (operation, Δα<0.05 dB) | EN 187000, Met. 601 | -25°C / +70°C Cycles=4 |
| Water penetration | EN 187000, Met. 605B | LP _{water} = 1 m (14 days) |

All drawings, designs, specifications and particulars of weights, dimensions, etc. in this documentation are only indicative and must not be considered contractual.



EE6102N- Ed1

512 OPTICAL FIBRES CABLE FOR DUCT INSTALLATION - KP TYPE

DIMENSIONS AND WEIGHT

| Code | No. fibres | Diameter (mm) | Nominal weight (kg/km) | |
|------------------|------------|---------------|------------------------|--|
| | | | | |
| EE6102N00051202N | 512 | 22,0 | 330 | |

All drawings, designs, specifications and particulars of weights, dimensions, etc. in this documentation are only indicative and must not be considered contractual.



page. 3/3