

Extralink kabel łatwego dostępu 24f G.657A2 500M



4,10 PLN brutto
3,33 PLN netto

Producent: EXTRALINK

FIBRE PROPERTIES			
CHARACTERISTICS		UNIT	VALUE
ATTENUATION	@ 1310 nm	dB/ km	< 0.36
	@ 1550 nm	dB/ km	< 0.22
PMD		dB(ps/km1/2)	< 0.2
CABLE CUT-OFF WAVELENGTH		nm	1260
ZERO-DISPERSION WAVELENGTH		nm	1300~1324
ZERO-DISPERSION SLOPE		dB(ps/km1/2)	< 0.092
CHROMATIC DISPERSION	@ 1285~1330 nm	ps/(nm^2.km)	< 3.5
	@ 1550 nm	ps/(nm^2.km)	< 18.0
MODE FIELD DIAMETER	@ 1310 nm	um	9.3 + 0.5
CORE/CLAD CONCENTRICITY ERROR		um	< 0.6
CLADDING DIAMETER		um	125.0 + 1.0
CLADDING NON-CIRCULARITY			< 1.0 %
PRIMARY COATING DIAMETER		um	245 + 10
PROOF TEST LEVEL		kpsi	100, 1%
MECHANICAL & ENVIRONMENTAL PROPERTIES			
CRUSH	Test method: IEC 60794-1-2 Method E3	Applied load: 500 N/100mm	
	Acceptance Criteria	Duration of loading: 5 minutes	
		Attenuation increment: < 0.2 dB	
INSTALLATION TEMPERATURE		-20°C to 70°C	
SERVICE TEMPERATURE		-20°C to 70°C	
STORAGE TEMPERATURE		-30°C to 70°C	
PHYSICAL & DIMENSIONS PROPERTIES			
NO. OF FIBRES		24 C	
TYPE OF FIBRE		HSCC-15-PAT001	
COLOUR OF FIBRE		blue/ orange/ green/ brown/ grey/ white/ red/ black	
		yellow/ violet/ pink/ aqua/ black-blue/ black-orange	
		black-green/ black-brown/ black-grey/ black-white	
		black-red/ white-black/ black-yellow/ black-violet	
		black-pink/ black-aqua	
PRIMARY COATING WITH COLOR LAYER		245 + 10 μm	
TIGHT BUFFER		900 μm tight buffer fiber	
REINFORCED STRENGTH MEMBER		KRP Rod	
OUTER JACKET		LSZH	
CABLE OUTER DIAMETER		10.5 + 0.5 nm	
STANDARD LENGTH		2 km + 10 %	

Do montażu	Wewnętrzny
Liczba włókien	24F
Rodzaj włókna	G.657.A2
Średnica kabla	-

